



**TBT**

**Typhoon Business Trading  
Stone Supplier**



*We Are Supplier*

# TRAVERTINE

*Best Quality*



**ADDRESS :**

**VILLA NO. 1121, WAY: 3709, SOUTH GHUBRA  
P.O BOX: 850, PC: 133 AL KHUWAIR  
MUSCAT-OMAN**



**0096879408000**

**WWW.TBT.OM**



**WWW.STONESUPPLIER.CO**

# Certificates



TECHNO CERT  
International Certification Body

**CERTIFICATE**  
Certificate No. 6195202342

It is hereby certify that

**Typhoon Business Trading (TBT) Co.**  
Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850, PC: 133 Al Khuwair,  
Muscat, Oman

Has been documented and found to be in accordance of  
**Quality Management — Customer Satisfaction —  
Guidelines for Complaints Handling in Organizations**  
With the requirements of  
**ISO 10002:2018**  
Activity scope of organization  
Construction and Urban Development  
Export and Import of all Construction Materials  
Export of Stones

Issue certificate date: 18 Sep 2023  
1st surveillance date: 18 Sep 2024  
2nd surveillance date: 18 Sep 2025  
Expiry date: 18 Sep 2026  
Managing director: Alois Degler  
Issued by TECHNO CERT assessment private limited  
TECHNO CERT is a member of International organization. (certification body)

**ISO 10002 :2018**

TECHNO CERT  
International Certification Body

**CERTIFICATE**  
Certificate No. 6195202328

It is hereby certify that

**Typhoon Business Trading (TBT) Co.**  
Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850, PC: 133 Al Khuwair,  
Muscat, Oman

Has been documented and found to be in accordance of  
Security Management Systems for the Supply Chain —  
Best Practices for Implementing Supply Chain Security, Assessments and Plans  
With the requirements of  
**ISO 28001:2007**  
Activity scope of organization  
Construction and Urban Development  
Export and Import of all Construction Materials  
Export of Stones

Issue certificate date: 18 Sep 2023  
1st surveillance date: 18 Sep 2024  
2nd surveillance date: 18 Sep 2025  
Expiry date: 18 Sep 2026  
Managing director: Alois Degler  
Issued by TECHNO CERT assessment private limited  
TECHNO CERT is a member of International organization. (certification body)

**ISO 28001 :2007**

TECHNO CERT  
International Certification Body

**CERTIFICATE**  
Certificate No. 6195202308

It is hereby certify that

**Typhoon Business Trading (TBT) Co.**  
Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850, PC: 133 Al Khuwair,  
Muscat, Oman

Has been documented and found to be in accordance of  
**Integrated Management System (IMS)**  
With the requirements of  
**ISO9001:2015 & ISO14001:2015 & ISO45001:2018**  
Activity scope of organization  
Construction and Urban Development  
Export and Import of all Construction Materials  
Export of Stones

Issue certificate date: 18 Sep 2023  
1st surveillance date: 18 Sep 2024  
2nd surveillance date: 18 Sep 2025  
Expiry date: 18 Sep 2026  
Managing director: Alois Degler  
Issued by TECHNO CERT assessment private limited  
TECHNO CERT is a member of International organization. (certification body)

**ISO 9001 :2015**

**G-CERTI Certificate**  
hereby certifies that

**Typhoon Business Trading (TBT) Co.**  
Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850, PC: 133 Al Khuwair,  
Muscat, Oman

meets the Standard Requirements & Scope as following

**ISO 9001:2015**  
Quality Management Systems

Construction and Urban Development  
Export and Import of all Construction Materials  
Export of Stones

Certificate No : GKIR-0772-QC Code : 28, 29  
Initial Date : 2023. 09. 18 Issue Date : 2023. 09. 18  
Expiry Date : 2026. 09. 17 Valid period : 2023. 09. 18 - 2024. 09. 17

Signed for and on behalf of GCERTI  
President I.K.Chou

**ISO 9001 :2015**

**G-CERTI Certificate**  
hereby certifies that

**Typhoon Business Trading (TBT) Co.**  
Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850, PC: 133 Al Khuwair,  
Muscat, Oman

meets the Standard Requirements & Scope as following

**ISO 45001:2018**  
Occupational Health and Safety Management Systems

Construction and Urban Development  
Export and Import of all Construction Materials  
Export of Stones

Certificate No : GKIR-0772-OHC Code : 28, 29  
Initial Date : 2023. 09. 18 Issue Date : 2023. 09. 18  
Expiry Date : 2026. 09. 17 Valid period : 2023. 09. 18 - 2024. 09. 17

Signed for and on behalf of GCERTI  
President I.K.Chou

**ISO 45001 :2018**

**G-CERTI Certificate**  
hereby certifies that

**Typhoon Business Trading (TBT) Co.**  
Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850, PC: 133 Al Khuwair,  
Muscat, Oman

meets the Standard Requirements & Scope as following

**ISO 14001:2015**  
Environmental Management Systems

Construction and Urban Development  
Export and Import of all Construction Materials  
Export of Stones

Certificate No : GKIR-0772-EC Code : 28, 29  
Initial Date : 2023. 09. 18 Issue Date : 2023. 09. 18  
Expiry Date : 2026. 09. 17 Valid period : 2023. 09. 18 - 2024. 09. 17

Signed for and on behalf of GCERTI  
President I.K.Chou

**ISO 14001 :2015**

Certificate No. 102-31223202-01  
Issue date: 13-Sep-2023

**(TUV) GROUP**

**VERIFICATION OF COMPLIANCE**

The TUV GROUP hereby declares that testing has been completed and report has been generated for:

Product name: Building Stone  
Model: —  
Applicant: Typhoon Business Trading (TBT)  
Address: Villa No. 1121, Way: 3709, South Ghubra, P.O Box: 850,  
PC: 133 Al Khuwair, Muscat, Oman

And, in accordance to the following applicable directive:  
89/106/EEC Construction Products

That this product has been tested according to the following standard(s):  
EN 1469:2015, BS EN 12059:2008 +A1:2011, EN 12440:2017

This verification of conformity is based on an evaluation of samples of the above products. The tests were performed in normal operation mode. Test results apply only to the particular sample tested and to the specific tests carried out. Technical report and documentation are at the holder's disposal.

This certificate was first issued on 13.09.2023 and will remain valid until 13.09.2026 as long as the test methods and/or factory production control requirements included in the harmonized standard, used to assess the performance of the declared characteristics, do not change, and the product, and the manufacturing conditions in the plant are not modified significantly.

CE (TUV) GROUP CERTIFIED Authorised Signature

**EN 12440 : 2017**

**TBT**  
Typhoon Business Trading  
Stone Supplier

**ADDRESS :**  
**VILLA NO. 1121, WAY: 3709, SOUTH GHUBRA**  
**P.O BOX: 850, PC: 133 AL KHUWAIR**  
**MUSCAT-OMAN**



**0096879408000**

**WWW.TBT.OM**



**WWW.STONESUPPLIER.CO**



**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine


**CODE : TT-01**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>871 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.67 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	-----	<b>POROSITY</b>	-----
<b>W.A</b>	<b>2.18 %</b>	<b>HARDNESS</b>	-----

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b> .....	<b>CaO</b> .....	<b>MgO</b> .....	<b>SiO<sub>2</sub></b> .....
<b>P<sub>2</sub>O<sub>5</sub></b> .....	<b>TiO<sub>2</sub></b> .....	<b>Fe<sub>2</sub>O<sub>3</sub></b> .....	<b>L.O.I</b> .....
<b>MnO</b> .....	<b>Na<sub>2</sub>O</b> .....	<b>Al<sub>2</sub>O<sub>3</sub></b> .....	



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-02**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>411.67 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.67 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	-----	<b>POROSITY</b>	-----
<b>W.A</b>	<b>2.18%</b>	<b>HARDNESS</b>	-----

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b> 0.01 %	<b>CaO</b> 54.09 %	<b>MgO</b> 0.76 %	<b>SiO<sub>2</sub></b> 0.63 %
<b>P<sub>2</sub>O<sub>5</sub></b> 0.059%	<b>TiO<sub>2</sub></b> 0.028 %	<b>Fe<sub>2</sub>O<sub>3</sub></b> 0.22 %	<b>L.O.I</b> 44.09%
<b>MnO</b> 0.001%	<b>Na<sub>2</sub>O</b> 0.01 %	<b>Al<sub>2</sub>O<sub>3</sub></b> 0.1 %	





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine


**CODE : TT-03**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>506 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.67 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>238 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>-----</b>
<b>W.A</b>	<b>2.4 %</b>	<b>HARDNESS</b>	<b>-----</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.09 %</b>	<b>CaO</b>	<b>51.87%</b>	<b>MgO</b>	<b>0.5 %</b>	<b>SiO<sub>2</sub></b>	<b>0.18 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....%</b>	<b>TiO<sub>2</sub></b>	<b>0.03 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>7.853%</b>	<b>L.O.I</b>	<b>38.91%</b>
<b>MnO</b>	<b>.....%</b>	<b>Na<sub>2</sub>O</b>	<b>0.04 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.06 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-04**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>320 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.49 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>300 kg/cm</b>	<b>POROSITY</b>	<b>5 %</b>
<b>W.A</b>	<b>0.7 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.05 %</b>	<b>CaO</b>	<b>54.45%</b>	<b>MgO</b>	<b>1.15 %</b>	<b>SiO<sub>2</sub></b>	<b>0.54 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.02 %</b>	<b>TiO<sub>2</sub></b>	<b>0.032%</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.19 %</b>	<b>L.O.I</b>	<b>42.75%</b>
<b>MnO</b>	<b>0.001%</b>	<b>Na<sub>2</sub>O</b>	<b>0.05 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.07 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-05**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>271 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.23 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>231 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>-----</b>
<b>W.A</b>	<b>5.56 %</b>	<b>HARDNESS</b>	<b>-----</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>-----</b>	<b>CaO</b>	<b>55.37%</b>	<b>MgO</b>	<b>-----</b>	<b>SiO<sub>2</sub></b>	<b>0.56 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>-----</b>	<b>TiO<sub>2</sub></b>	<b>-----</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.9 %</b>	<b>L.O.I</b>	<b>-----</b>
<b>MnO</b>	<b>-----</b>	<b>Na<sub>2</sub>O</b>	<b>0.11 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>1.6 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-06**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>460 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.53 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>440 kg/cm</b>	<b>POROSITY</b>	<b>0.06 %</b>
<b>W.A</b>	<b>1.30 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.02 %</b>	<b>CaO</b>	<b>54.87 %</b>	<b>MgO</b>	<b>0.44 %</b>	<b>SiO<sub>2</sub></b>	<b>0.59 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.075 %</b>	<b>TiO<sub>2</sub></b>	<b>0.010 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.06 %</b>	<b>L.O.I</b>	<b>43.36 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.04 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.16 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-07**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>680 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.52 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>650 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>5 %</b>
<b>W.A</b>	<b>0.37 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.02 %</b>	<b>CaO</b>	<b>54.9 %</b>	<b>MgO</b>	<b>0.68 %</b>	<b>SiO<sub>2</sub></b>	<b>0.33 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.016 %</b>	<b>TiO<sub>2</sub></b>	<b>0.026 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.12 %</b>	<b>L.O.I</b>	<b>43.45 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.05 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.03 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-08**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>710 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.52 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>690 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>8 %</b>
<b>W.A</b>	<b>0.31 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.06 %</b>	<b>CaO</b>	<b>54.64 %</b>	<b>MgO</b>	<b>0.77 %</b>	<b>SiO<sub>2</sub></b>	<b>0.62 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.026 %</b>	<b>TiO<sub>2</sub></b>	<b>0.031 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.22 %</b>	<b>L.O.I</b>	<b>42.98 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.01 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.02 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-09**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>480 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.42 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>315 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>3 %</b>
<b>W.A</b>	<b>.....</b>	<b>HARDNESS</b>	<b>.....</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>.....</b>	<b>CaO</b>	<b>55.03%</b>	<b>MgO</b>	<b>0.12 %</b>	<b>SiO<sub>2</sub></b>	<b>0.52 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.59 %</b>	<b>L.O.I</b>	<b>43.7 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>.....</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>.....</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-10**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>590 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.55 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>550 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>9 %</b>
<b>W.A</b>	<b>0.11 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.07 %</b>	<b>CaO</b>	<b>52.95 %</b>	<b>MgO</b>	<b>0.11 %</b>	<b>SiO<sub>2</sub></b>	<b>2.1 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>1.31 %</b>	<b>L.O.I</b>	<b>42.81 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>0.03 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.53 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-11**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>660 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.6 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>640 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>8 %</b>
<b>W.A</b>	<b>0.2 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.09</b>	<b>CaO</b>	<b>50.64 %</b>	<b>MgO</b>	<b>0.42 %</b>	<b>SiO<sub>2</sub></b>	<b>4.95 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>0.023%</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>1.78 %</b>	<b>L.O.I</b>	<b>40.59 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>0.04 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>1.32 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-12**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>600 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.5 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>570 kg/cm</b>	<b>POROSITY</b>	<b>5 %</b>
<b>W.A</b>	<b>0.22 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.04 %</b>	<b>CaO</b>	<b>55.23 %</b>	<b>MgO</b>	<b>0.47 %</b>	<b>SiO<sub>2</sub></b>	<b>0.27 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.017%</b>	<b>TiO<sub>2</sub></b>	<b>0.029%</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.2 %</b>	<b>L.O.I</b>	<b>43.32 %</b>
<b>MnO</b>	<b>0.001%</b>	<b>Na<sub>2</sub>O</b>	<b>0.02 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.04 %</b>		







**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-13**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>737.25 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.40 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	.....	<b>POROSITY</b>	.....
<b>W.A</b>	<b>1.53 %</b>	<b>HARDNESS</b>	.....

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.02 %</b>	<b>CaO</b>	<b>55.19 %</b>	<b>MgO</b>	<b>0.35 %</b>	<b>SiO<sub>2</sub></b>	<b>1.57 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.013 %</b>	<b>TiO<sub>2</sub></b>	<b>0.007 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.44 %</b>	<b>L.O.I</b>	<b>41.84 %</b>
<b>MnO</b>	<b>0.003 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.4 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.16 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-14**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>778 kg/cm<sup>3</sup></b>	<b>DENSITY</b>	<b>2.664 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>543 kg/cm<sup>3</sup></b>	<b>POROSITY</b>	.....
<b>W.A</b>	<b>1.72 %</b>	<b>HARDNESS</b>	.....

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	.....	<b>CaO</b>	<b>51.8 %</b>	<b>MgO</b>	<b>4.7 %</b>	<b>SiO<sub>2</sub></b>	<b>5.8 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	.....	<b>TiO<sub>2</sub></b>	.....	<b>Fe<sub>2</sub>O<sub>3</sub></b>	.....	<b>L.O.I</b>	.....
<b>MnO</b>	.....	<b>Na<sub>2</sub>O</b>	.....	<b>Al<sub>2</sub>O<sub>3</sub></b>	.....		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-15**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>680 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.57 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>660 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>4 %</b>
<b>W.A</b>	<b>0.85 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.03 %</b>	<b>CaO</b>	<b>54.63 %</b>	<b>MgO</b>	<b>0.44 %</b>	<b>SiO<sub>2</sub></b>	<b>0.21 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.015 %</b>	<b>TiO<sub>2</sub></b>	<b>0.031 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>1.16 %</b>	<b>L.O.I</b>	<b>42.87 %</b>
<b>MnO</b>	<b>0.061 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.02 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.02 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-16**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>510 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.54 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>303 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>5.05 %</b>
<b>W.A</b>	<b>2.09 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.04 %</b>	<b>CaO</b>	<b>55.16 %</b>	<b>MgO</b>	<b>.....</b>	<b>SiO<sub>2</sub></b>	<b>.....</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.06 %</b>	<b>L.O.I</b>	<b>44.03 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>0.61 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>.....</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-17**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>400 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.67 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>380 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>5 %</b>
<b>W.A</b>	<b>0.21 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.01 %</b>	<b>CaO</b>	<b>55.94 %</b>	<b>MgO</b>	<b>0.33 %</b>	<b>SiO<sub>2</sub></b>	<b>0.11 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.007 %</b>	<b>TiO<sub>2</sub></b>	<b>0.001 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.07 %</b>	<b>L.O.I</b>	<b>43.16 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.12 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.02 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-18**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>540 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.44 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>520 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>8 %</b>
<b>W.A</b>	<b>0.9 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.03 %</b>	<b>CaO</b>	<b>54.17 %</b>	<b>MgO</b>	<b>0.39 %</b>	<b>SiO<sub>2</sub></b>	<b>1.51 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.018 %</b>	<b>TiO<sub>2</sub></b>	<b>0.009 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.41 %</b>	<b>L.O.I</b>	<b>42.41 %</b>
<b>MnO</b>	<b>0.003 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.34 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.14 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-19**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>560 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.49 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>550 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>8 %</b>
<b>W.A</b>	<b>0.05 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.03 %</b>	<b>CaO</b>	<b>54.77 %</b>	<b>MgO</b>	<b>0.31 %</b>	<b>SiO<sub>2</sub></b>	<b>0.75 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.09 %</b>	<b>L.O.I</b>	<b>43.36 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>0.1 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.38 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier


**CODE : TT-20**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>500 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.507 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>480 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>8 %</b>
<b>W.A</b>	<b>0.25 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.04 %</b>	<b>CaO</b>	<b>54.45 %</b>	<b>MgO</b>	<b>0.61 %</b>	<b>SiO<sub>2</sub></b>	<b>0.22 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.019 %</b>	<b>TiO<sub>2</sub></b>	<b>0.027 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.16 %</b>	<b>L.O.I</b>	<b>43.75 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.03 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.08 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-21**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>532 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.43 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>451 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>1.4 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>.....</b>	<b>CaO</b>	<b>54.26 %</b>	<b>MgO</b>	<b>.....</b>	<b>SiO<sub>2</sub></b>	<b>.....</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.10 %</b>	<b>L.O.I</b>	<b>44.38 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>.....</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.2 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-22**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>460 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.5 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>440 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>10 %</b>
<b>W.A</b>	<b>0.25 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.01 %</b>	<b>CaO</b>	<b>55.39 %</b>	<b>MgO</b>	<b>0.15 %</b>	<b>SiO<sub>2</sub></b>	<b>0.21 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.04 %</b>	<b>TiO<sub>2</sub></b>	<b>0.001 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.04 %</b>	<b>L.O.I</b>	<b>43.54 %</b>
<b>MnO</b>	<b>0.002 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.23 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.01 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-23**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>490 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.7 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>415 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>0.7 %</b>	<b>HARDNESS</b>	<b>.....</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>.....</b>	<b>CaO</b>	<b>53.98 %</b>	<b>MgO</b>	<b>35 %</b>	<b>SiO<sub>2</sub></b>	<b>1.12 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>1.63 %</b>	<b>L.O.I</b>	<b>42.96 %</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>.....</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>.....</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-24**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>460 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.53 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>440 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>0.06 %</b>
<b>W.A</b>	<b>1.30 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.02 %</b>	<b>CaO</b>	<b>54.87 %</b>	<b>MgO</b>	<b>0.44 %</b>	<b>SiO<sub>2</sub></b>	<b>0.59 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.075 %</b>	<b>TiO<sub>2</sub></b>	<b>0.010 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.06 %</b>	<b>L.O.I</b>	<b>43.36 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.04 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.16 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-25**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>892 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.69 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>780 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>5.97 %</b>
<b>W.A</b>	<b>2.41 %</b>	<b>HARDNESS</b>	<b>3_3.5</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.03 %</b>	<b>CaO</b>	<b>51.49 %</b>	<b>MgO</b>	<b>2.38 %</b>	<b>SiO<sub>2</sub></b>	<b>0.47 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.041 %</b>	<b>TiO<sub>2</sub></b>	<b>0.14 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.95 %</b>	<b>L.O.I</b>	<b>43.71 %</b>
<b>MnO</b>	<b>0.016 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.03 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.64 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-26**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>240 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.47 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>200 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>0.04 %</b>
<b>W.A</b>	<b>1.25 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.01 %</b>	<b>CaO</b>	<b>55.09 %</b>	<b>MgO</b>	<b>0.36 %</b>	<b>SiO<sub>2</sub></b>	<b>0.21 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.072 %</b>	<b>TiO<sub>2</sub></b>	<b>0.001 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.01 %</b>	<b>L.O.I</b>	<b>44.01 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.02 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.03 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-27**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>557.2 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.4 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>543 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>2.3 %</b>	<b>HARDNESS</b>	<b>3.8</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.97 %</b>	<b>CaO</b>	<b>53.28 %</b>	<b>MgO</b>	<b>0.37 %</b>	<b>SiO<sub>2</sub></b>	<b>0.28 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.69 %</b>	<b>TiO<sub>2</sub></b>	<b>0.08 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>3.24 %</b>	<b>L.O.I</b>	<b>.....</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>1.15 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>2.31 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-28**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>461 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.42 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>349 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>2.423 %</b>	<b>HARDNESS</b>	<b>6_6.5</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.03 %</b>	<b>CaO</b>	<b>65.22 %</b>	<b>MgO</b>	<b>0.49 %</b>	<b>SiO<sub>2</sub></b>	<b>0.21 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.029 %</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.17 %</b>	<b>L.O.I</b>	<b>43.11 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>.....</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.09 %</b>		







**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-29**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>470 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.57 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>450 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>2.4 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.02 %</b>	<b>CaO</b>	<b>53.24 %</b>	<b>MgO</b>	<b>0.3 %</b>	<b>SiO<sub>2</sub></b>	<b>0.5 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.07 %</b>	<b>TiO<sub>2</sub></b>	<b>0.01 %</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>1.31 %</b>	<b>L.O.I</b>	<b>44.40 %</b>
<b>MnO</b>	<b>0.01 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.04 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.1 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-30**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>120 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.67 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>110 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>7 %</b>
<b>W.A</b>	<b>1.1 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.03 %</b>	<b>CaO</b>	<b>.....</b>	<b>MgO</b>	<b>0.45 %</b>	<b>SiO<sub>2</sub></b>	<b>0.31 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.019 %</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.15 %</b>	<b>L.O.I</b>	<b>43.17 %</b>
<b>MnO</b>	<b>0.001 %</b>	<b>Na<sub>2</sub>O</b>	<b>0.05 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.05 %</b>		





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-31**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>436 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.313 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>307 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>8.9 %</b>
<b>W.A</b>	<b>3.88 %</b>	<b>HARDNESS</b>	<b>.....</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b> .....	<b>CaO</b> 55.4 %	<b>MgO</b> .....	<b>SiO<sub>2</sub></b> .....
<b>P<sub>2</sub>O<sub>5</sub></b> .....	<b>TiO<sub>2</sub></b> .....	<b>Fe<sub>2</sub>O<sub>3</sub></b> .....	<b>L.O.I</b> 43.6 %
<b>MnO</b> .....	<b>Na<sub>2</sub>O</b> .....	<b>Al<sub>2</sub>O<sub>3</sub></b> .....	



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-32**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>400 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.48 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>380 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>6 %</b>
<b>W.A</b>	<b>0.67 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b> 0.03 %	<b>CaO</b> 55.27 %	<b>MgO</b> 0.45 %	<b>SiO<sub>2</sub></b> 0.23 %
<b>P<sub>2</sub>O<sub>5</sub></b> 0.015 %	<b>TiO<sub>2</sub></b> 0.023 %	<b>Fe<sub>2</sub>O<sub>3</sub></b> 0.31 %	<b>L.O.I</b> 42.96 %
<b>MnO</b> 0.059 %	<b>Na<sub>2</sub>O</b> 0.06 %	<b>Al<sub>2</sub>O<sub>3</sub></b> 0.01 %	





**TBT**  
Typhoon Business Trading  
Stone Supplier

# Travertine

**CODE : TT-33**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>360 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.55 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>3.50 kg/cm<sup>2</sup></b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>0.05 %</b>	<b>HARDNESS</b>	<b>3</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>0.01%</b>	<b>CaO</b>	<b>54.09 %</b>	<b>MgO</b>	<b>0.76 %</b>	<b>SiO<sub>2</sub></b>	<b>0.63 %</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>0.059%</b>	<b>TiO<sub>2</sub></b>	<b>0.028%</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.17 %</b>	<b>L.O.I</b>	<b>43.8 %</b>
<b>MnO</b>	<b>0.001%</b>	<b>Na<sub>2</sub>O</b>	<b>0.01 %</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>0.1 %</b>		



**TBT**  
Typhoon Business Trading  
Stone Supplier

**CODE : TT-34**

## PHYSICAL PROPERTIES

<b>D.S.C</b>	<b>900.79 kg/cm<sup>2</sup></b>	<b>DENSITY</b>	<b>2.66 gr/cm<sup>3</sup></b>
<b>W.C.S</b>	<b>.....</b>	<b>POROSITY</b>	<b>.....</b>
<b>W.A</b>	<b>2.04 %</b>	<b>HARDNESS</b>	<b>.....</b>

## CHEMICAL ANALYSIS

<b>K<sub>2</sub>O</b>	<b>.....</b>	<b>CaO</b>	<b>.....</b>	<b>MgO</b>	<b>.....</b>	<b>SiO<sub>2</sub></b>	<b>.....</b>
<b>P<sub>2</sub>O<sub>5</sub></b>	<b>.....</b>	<b>TiO<sub>2</sub></b>	<b>.....</b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>.....</b>	<b>L.O.I</b>	<b>.....</b>
<b>MnO</b>	<b>.....</b>	<b>Na<sub>2</sub>O</b>	<b>.....</b>	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>.....</b>		

